



FHT-ST

Features

- Made from FDA-sanctioned ingredients
- Able to resist extreme temperature variation: -100°F to 500°F
- Translucent for visual contact with the flow
- Resilient, Odorless, tasteless, stretchable, and resistant to compression set, U.V., ozone, moisture and gas



Silicone Tubing

Materials For Industry

FHT-ST Silicone Rubber Tubing						
PART NUMBER	INSIDE DIAMETER	OUTSIDE DIAMETER	WALL THICKNESS	WORKING PSI AT 70°F	BURST PSI AT 70°F	
FHT-ST125L-XXX	.125"	.187"	.031"	10	30	100 FT
FHT-ST125T-XXX	.125"	.250"	.062"	20	60	100 FT
FHT-ST125S-XXX	.125"	.312"	.093"	25	75	100 FT
FHT-ST125H-XXX	.125"	.375"	.125"	15	45	100 FT
FHT-ST187L-XXX	.187"	.250"	.031"	5	15	100 FT
FHT-ST187T-XXX	.187"	.312"	.062"	20	60	100 FT
FHT-ST187S-XXX	.187"	.375"	.093"	20	60	100 FT
FHT-ST187H-XXX	.187"	.434"	.125"	15	45	100 FT
FHT-ST250L-XXX	.250"	.312"	.031"	10	30	100 FT
FHT-ST250T-XXX	.250"	.375"	.062"	5	15	100 FT
FHT-ST250S-XXX	.250"	.434"	.093"	20	60	100 FT
FHT-ST250H-XXX	.250"	.500"	.125"	15	45	100 FT
FHT-ST375L-XXX	.375"	.500"	.062"	10	30	100 FT
FHT-ST375T-XXX	.375"	.562"	.093"	10	30	100 FT
FHT-ST375S-XXX	.375"	.625"	.125"	10	30	100 FT
FHT-ST375H-XXX	.375"	.750"	.187"	15	45	100 FT
FHT-ST500L-XXX	.500"	.625"	.062"	5	15	100 FT
FHT-ST500T-XXX	.500"	.685"	.093"	5	15	100 FT
FHT-ST500S-XXX	.500"	.750"	.125"	10	30	100 FT
FHT-ST500H-XXX	.500"	.875"	.187"	10	30	100 FT

Standard colors: Natural
Packaging - spools

Ordering Info: (Type of material) (size) (wall) (color)
FHT-ST 125 L NAT

Technical Data

Physical Properties

Hardness Shore D	50	Tensile Strength, min PSI	1100
Elongation at Break, %	375	Brittle Temp, °F	<-100
Max Operating Temp, °F	500		

Source Associates, Inc.
(408)970-0128 Fax (408)970-9748
www.source.as e-mail: sales@source.as